

**Unitex**

22 Park Drive
Dandenong VIC 3175

Phone: (03) 9768 4900
Fax (03) 9768 4999
www.unitex.com.au

Unitex (NSW)

14 Artisan Road
Seven Hills NSW 2147

Phone: (02) 9838 0911
Fax (02) 9838 9555
www.unitex.com.au

URW (Oakleigh)

1346 North Road
Oakleigh VIC 3167

Phone: 1800 RENDER
Fax (03) 9544 3620
www.render.com.au

URW (SA)

2/54-56 Cavan Road
Dry Creek SA 5094

Phone: 1800 RENDER
Fax (08) 8262 7922
www.render.com.au

Technical Data Sheet

Unitex® Beach Render Render

Blended dry powder render for trowel-applied one or two coat applications over new and old brick as well as cement block.

Description

Unitex® Beach Render Render is a cement-based blended powder that when mixed thoroughly with water, can be trowel applied and sponge finished in typical thicknesses of 2-10 mm over masonry surfaces such as new and old bricks and concrete block-work.

For the discerning project managers, builders and applicators, Unitex® Beach Render Render assists your project as follows:

Trowels on easily and smoothly in thin layers.

Is polymer-modified for strong adhesion to masonry surfaces.

Is more waterproof than conventional render.

Easily prepared. Just add water and drill to your preferred consistency.

Is ideal for renovation works or over new surfaces.

Consistent quality.

After drying, can be overcoated with a tinted Unitex Applied Texture Finish.

Is readily available in paper sacks individually or on 60 sack pallets.

Is manufactured by Unitex in Australia.

Uses

Unitex® Beach Render Render is trowel applied and suitable for a one coat or two coat application on all suitable masonry surfaces, e.g. brick or block, etc. both inside and out, and is recommended to aid in the protection of masonry walls from the damaging effect of surface ingress of moisture. If the surface is in good order, only a skim coat is required.

Unitex® Beach Render Render is cement based and polymer modified for water resistance and strong adhesion to sound masonry surfaces. Unitex® Beach Render Render is applied either mechanically sprayed or trowelled and then rubbed up to a true and even surface with a float. This product is workable at thicknesses of 2 mm up to approximately 10 mm.

Unitex® Beach Render Render enhances the appearance of masonry surfaces and may be sponge finished for a concrete "olde worlde" sandy surface effect. As well, Unitex® Beach Render Render can be trowel applied, finished with a float and overcoated with Unitex Applied Finishes such as factory tinted Uni-Trowel Décor 146 (fine marble finish), 155 (medium marble finish), 333 (medium sand finish) or 777 (enhanced medium marble finish) "wet" textures or Uni-Cote 846 (fine marble finish) or 855 (medium marble finish) dry powder textures. After the texture is dry, a suitable factory tinted topcoat such as Uni-PTC can be applied for added protection against weather effects.

Unitex® Beach Render Render is supplied in ready-to-use 20 kg bags. Each bag allows up to 15 litres of wet render to be prepared by mixing the bag contents with approximately 4-5 litres of clean water and drilling for homogeneity.

Coverage per bag depends on the desired thickness of the render and at a low-build thickness of 4 mm., coverage of approximately 2 m² can be expected.

TECHNICAL DATA SHEET

CLADDING | RENDERS | TEXTURES | MOULDINGS + COLUMNS | ACCESSORIES

Unitex Granular Marble Pty Ltd ACN 005 995 611 ABN 42 087 324 477

Unitex Render Warehouse (SA) Pty Ltd ACN 601 059 929 ABN 96 601 059 929



Unitex
22 Park Drive
Dandenong VIC 3175

Phone: (03) 9768 4900
Fax (03) 9768 4999
www.unitex.com.au

Unitex (NSW)
14 Artisan Road
Seven Hills NSW 2147

Phone: (02) 9838 0911
Fax (02) 9838 9555
www.unitex.com.au

URW (Oakleigh)
1346 North Road
Oakleigh VIC 3167

Phone: 1800 RENDER
Fax (03) 9544 3620
www.render.com.au

URW (SA)
2/54-56 Cavan Road
Dry Creek SA 5094

Phone: 1800 RENDER
Fax (08) 8262 7922
www.render.com.au

Application Instructions

Substrates

Masonry surfaces such as new or old brickwork and concrete block-work .

Substrate condition

Before application of any render, the masonry surface must be clean, dry, cured and free of any dust and debris. This means that any loose or damaged substrate must be removed, or patched and repaired, and any moisture must also evaporate out prior to Unitex® Beach Render Render being trowelled onto the substrate.

Ensure that the surface is clean and dry. All surfaces must be free of efflorescence, grease, oil, mould, dirt, dust, release agents, bond-breakers or other contaminants that may interfere with adhesion. Pre-painted substrates must be wire brushed back to the bare substrate.

Adequate expansion joints are required to minimize cracking on the surface of the render. Location of the expansion joints is the responsibility of the Builder or Head Contractor. Unitex® recommends expansion joints to every elevation and between different substrates to allow for building movements and stresses. If such expansion joints are not provided, cracking due to movement of the substrate may occur. This is in no way indicative of faulty material. Rather it indicates sub-standard building practice.

All substrates must be dry before render is applied and conversely, all render surfaces must be dry before being over-coated. Unitex recommends testing surface dryness with a Moisture Meter (such as Protimeter) where the WME (Wood Moisture Equivalent) must be lower than 15 %.

Note: A test area of the complete Unitex® system must always be provided by the applicator for the Builder and Specifier approval.

Always contact Unitex® for specific substrate specifications.

Site Preparation

It is important to ensure that, as well as the substrate being properly prepared, the work area is also made ready. This means masking and protective covering of windows, doors and adjoining surfaces to avoid marking the glass and frame surfaces with splatter. Drop sheets should also be used where required (tiles, pavers, downpipes, etc.).

Building regulations, if the scope of work invokes these, will require scaffolding to be erected by a qualified and certified operator. Equipment must be tagged and kept in good safe working order. Site and local handling of equipment regulations must be followed to provide a safe work environment.

Weather Conditions

If temperatures are less than 8 °C or greater than 30°C, Unitex® Beach Render Render should not be applied to a wall.

Freshly applied Unitex® Beach Render Render must be protected from rain, other sources of moisture and frosts for at least 48 hours.

Mixing

As a cement-containing blended powder, Unitex® Beach Render Render must be thoroughly mixed with clean, potable water to an homogenous slurry prior to application. As the cement cures, the slurry will get thicker with time until it is no longer useable. The pot life is about 3 hours in ambient conditions.

Mechanical stirrers are recommended for mixing powder into water. Whilst the water content and flow of the slurry should vary slightly for different weather conditions (try for a little more water on days of higher temperatures), a good guide is to use 3 volumes of Unitex® Beach Render Render to one volume of water, that is, use approx. 4.5 litres of water to 1 bag of render. Unitex® Beach Render Render must always be mixed into water: not the other way around. Note that there is a useable application time (pot life) of about 3 hours before the slurry is no longer workable. Addition of too much water will result in shrinkage and cracking.

TECHNICAL DATA SHEET

CLADDING | RENDERS | TEXTURES | MOULDINGS + COLUMNS | ACCESSORIES

Unitex Granular Marble Pty Ltd ACN 005 995 611 ABN 42 087 324 477

Unitex Render Warehouse (SA) Pty Ltd ACN 601 059 929 ABN 96 601 059 929

**Unitex**

22 Park Drive
Dandenong VIC 3175

Phone: (03) 9768 4900
Fax (03) 9768 4999
www.unitex.com.au

Unitex (NSW)

14 Artisan Road
Seven Hills NSW 2147

Phone: (02) 9838 0911
Fax (02) 9838 9555
www.unitex.com.au

URW (Oakleigh)

1346 North Road
Oakleigh VIC 3167

Phone: 1800 RENDER
Fax (03) 9544 3620
www.render.com.au

URW (SA)

2/54-56 Cavan Road
Dry Creek SA 5094

Phone: 1800 RENDER
Fax (08) 8262 7922
www.render.com.au

Application

Unitex® Beach Render Render is workable in low and high builds of 2-10 mm that can be trowelled over masonry surfaces in single or two passes. Sponging in a smooth, circular motion is recommended for a smooth, hole-free continuous surface.

Unitex® Beach Render Render is also suitable for spraying by pumpable render machines.

Unitex® Beach Render Render is not suitable as a render for use on expanded polystyrene (EPS) sheets: for this we recommend Unitex Polymer Render (with 5 % added cement) on uncoated EPS board or, for a CodeMark compliant and BRANZ Appraised wall solution, a choice of Unitex® Base Board Render or the lightweight product Unitex® “BBR 8.5 kg” on our factory coated Uni-Base Board EPS board. Unitex® “BBR 8.5 kg” can be trowelled in a single application at 6-8 mm thickness to achieve a Bushfire Attack Level of BAL-29 and at 12-14 mm thickness for BAL-40 (see Unitex meets BAL tests brochure).

Drying

In dry, mild conditions, Unitex® Beach Render Render should be dry after 72 hours after application. With certain site conditions such as shaded areas, lower temperatures or high humidity, drying of the render may take longer, even up to 7-10 days. Being a cement-containing product, maximum physical strength will not be achieved until 4 weeks have passed.

Always check the weather forecast before applying renders to masonry surfaces as rain, especially within the first 8 hours after application, has a tendency to damage or weaken the render, or at best, leave water marks. Heavy rain at any time in the first 2-3 weeks may leave water marks on the surface. Should rain damage occur, the render integrity and adhesion must be checked, and any necessary repairs carried out and then allowed to fully dry prior to allowing Unitex® Beach Render Render to be overcoated.

Both frosty conditions and excessively high temperatures should be avoided. Unitex recommends applying Unitex® Beach Render Render in temperatures above 8 °C and less than 30 °C. Should hot and windy conditions be encountered after commencing rendering, dampen the substrate with water. Do not apply render until the “wet” look has receded and the surface has absorbed the free water. This will enable Unitex® Beach Render Render to remain as workable as it is in milder conditions.

All substrates must be dry before render is applied and conversely, all render surfaces must be dry before being over-coated. Unitex recommends testing surface dryness with a Moisture Meter (such as Protimeter) where the WME (Wood Moisture Equivalent) must be lower than 15 %.

Cleaning up

All of the equipment used to apply Unitex Renders, Textures and Paints are cleaned up with water and a little “elbow grease” immediately after use. Cleaning should only be carried out at the Builder’s, or own, supplied environmental cleaning station where all waste water is captured for eventual removal to recycling stations.

Estimating**Supply**

Unitex® Beach Render Render 20 kg bag
60 bags per pallet

Coverage

Approximately 2 m² at 4 mm thickness.

Shelf Life

This product contains cement and must be kept dry. A shelf life of 6 months is to be expected. Discard partly filled open bags within 2 weeks of use.

TECHNICAL DATA SHEET

CLADDING | RENDERS | TEXTURES | MOULDINGS + COLUMNS | ACCESSORIES

Unitex Granular Marble Pty Ltd ACN 005 995 611 ABN 42 087 324 477

Unitex Render Warehouse (SA) Pty Ltd ACN 601 059 929 ABN 96 601 059 929



Unitex
22 Park Drive
Dandenong VIC 3175

Phone: (03) 9768 4900
Fax (03) 9768 4999
www.unitex.com.au

Unitex (NSW)
14 Artisan Road
Seven Hills NSW 2147

Phone: (02) 9838 0911
Fax (02) 9838 9555
www.unitex.com.au

URW (Oakleigh)
1346 North Road
Oakleigh VIC 3167

Phone: 1800 RENDER
Fax (03) 9544 3620
www.render.com.au

URW (SA)
2/54-56 Cavan Road
Dry Creek SA 5094

Phone: 1800 RENDER
Fax (08) 8262 7922
www.render.com.au

Product Safety

See MSDS

Unitex® Beach Render Render is classified as hazardous according to the criteria of NOHSC.

The product contains Portland cement. Portland cement is classified as a Hazardous Substance, Non-Dangerous Goods according to the criteria of NOHSC. All other components are classified as Non Hazardous, Non Dangerous Goods.

Risk phrases for Portland cement are

R36/37/38	Irritating to eyes, respiratory system and skin
R40	Possible risk of irreversible effects
R43	May cause sensitization by skin contact
R48/20	Harmful: danger of serious damage to health by prolonged exposure through inhalation

Safety Phrases for Portland cement

S22	Do not breathe dust
S24/25	Avoid contact with skin and eyes
S36/37	Wear suitable protective clothing and gloves

The chemical composition of Portland cement is essentially oxides of various elements, the most prevalent being oxides of calcium Ca, silica Si, aluminium Al, iron Fe, titanium Ti, chromium Cr (mostly as insoluble Cr III but it is possible that water soluble Cr IV could be present at concentrations of less than 10 ppm). Trace amounts of oxides of magnesium Mg, potassium K and phosphorus P may also be present. As cement is a blended product, crystalline silica at levels less than 0.1 % may be present.

Not classified as dangerous goods according to the Australian Code for Transport of Dangerous Goods.
NON DANGEROUS GOODS

Manufacturer's Details

Company Unitex Granular Marble Pty Ltd
22 Park Drive
Dandenong, Vic. 3175
Australia

Telephone +61 3 9768 4900
Telefax +61 3 9768 4999
Website www.unitex.com.au

Date issued 07 July 2014

This information contained herein relates only to the specific material identified. Unitex Granular Marble Pty Ltd believes that such information is accurate and reliable as of the date of this Technical Data Sheet, but no representation, guarantee or warranty, expressed or implied, is made to the accuracy, reliability or completeness of the information. Unitex urges persons receiving this information to make their own determination as to the information's suitability and completeness for their particular application.

TECHNICAL DATA SHEET

CLADDING | RENDERS | TEXTURES | MOULDINGS + COLUMNS | ACCESSORIES
Unitex Granular Marble Pty Ltd ACN 005 995 611 ABN 42 087 324 477
Unitex Render Warehouse (SA) Pty Ltd ACN 601 059 929 ABN 96 601 059 929