

Unitex® Coating Specification over Nasahi Panel

Introduction:

Please find following the Unitex coating specifications over the correctly installed Nasahi Panel (For installation guidelines please contact the board system provider).

The Nasahi Panel surface is to be dry, dust/powder/oil free, and fully cured (through dried). Once the above requirements have been met, please follow the below specifications.

Application steps:

1. Coat entire surface with Unitex Cembond as required or wash down walls to ensure dust/powder free.
2. Coat entire surface with Unitex Fast R Render or Unitex Aero Render and imbed Unitex Uni-Mesh to entire rendered surface. Ensure lengths of Uni-Mesh overlap by a minimum of 100mm. (Apply a second coat of Unitex Fast R Render or Unitex Aero Render as required). Allow to dry to 10-12%WME.
3. Drying times will vary depending on build-up of render and external weather conditions. Unitex recommends 10-12%WME is an acceptable level of dryness prior to application of texture coat. This moisture level can be checked with a moisture meter.
4. Apply one coat of chosen Unitex Texture to entire surface and allow to dry to 10-12%WME.
5. A recommended minimum of two coats of Unitex coloured Protective Top Coat can then be applied.



Unitex
22 Park Drive
Dandenong VIC 3175

Phone: (03) 9768 4900
Fax (03) 9768 4999
www.unitex.com.au

Unitex (NSW)
14 Artisan Road
Seven Hills NSW 2147

Phone: (02) 9838 0911
Fax (02) 9838 9555
www.unitex.com.au

URW (Oakleigh)
1346 North Road
Oakleigh VIC 3167

Phone: 1800 RENDER
Fax (03) 9544 3620
www.render.com.au

URW (SA)
20 Cardiff Court
Cavan SA 5094

Phone: (08) 8262 7900
Fax (08) 8262 7922
www.render.com.au

Always check with the builder:

All expansion, control and cosmetic joints are to be nominated by and are the responsibility of the builder – for only he and his engineer / architect etc. and base system provider can predict likely building and surface effect movement. An allowance for more rather than less expansion/contraction joints provides the greatest opportunity for a quality finish by the applicator and prevention of structural movement cracking.

Provide a sample area:

As always, the applicator is to trial a complete system sample area of minimum 2m² for builder's approval of system, colour, and applicator quality, before proceeding with the specified project.

Unitex® Product Information, TDS and MSDS documents:

All Unitex® products are thoroughly documented, and Technical Data Sheets and Material Safety Data Sheets are available through your Unitex Technical Representative, or via the Unitex® websites: www.unitex.com.au and www.render.com.au



Unitex
22 Park Drive
Dandenong VIC 3175

Phone: (03) 9768 4900
Fax (03) 9768 4999
www.unitex.com.au

Unitex (NSW)
14 Artisan Road
Seven Hills NSW 2147

Phone: (02) 9838 0911
Fax (02) 9838 9555
www.unitex.com.au

URW (Oakleigh)
1346 North Road
Oakleigh VIC 3167

Phone: 1800 RENDER
Fax (03) 9544 3620
www.render.com.au

URW (SA)
20 Cardiff Court
Cavan SA 5094

Phone: (08) 8262 7900
Fax (08) 8262 7922
www.render.com.au